

### NHG低熔点玻璃模压前后谱线折射率对照参考值

牌号	分类	n1064	nt	ns	nA'	nr	nC	nC'	nHe-Ne	nD	nd	ne	nF	nF'	ng	nh	ni	vd
		1064.00	1013.98	852.11	768.19	706.52	656.27	643.85	632.8	589.29	587.56	546.07	486.13	479.99	435.84	404.66	365.01	
D-PK61	模压前(-30℃/H)	1.48965	1.49010	1.49183	1.49301	1.49407	1.49514	1.49543	1.49571	1.49694	1.49700	1.49845	1.50123	1.50157	1.50451	1.50721	1.51173	81.61
	模压后	1.48840	1.48888	1.49066	1.49184	1.49291	1.49396	1.49426	1.49454	1.49576	1.49582	1.49727	1.50004	1.50039	1.50332	1.50601	1.51053	81.55
D-FK90	模压前(-30℃/H)	1.45238	1.45277	1.45425	1.45524	1.45615	1.45704	1.45729	1.45752	1.45855	1.45860	1.45981	1.46212	1.46241	1.46486	1.46710	1.47085	90.19
	模压后	1.45130	1.45173	1.45328	1.45429	1.45520	1.45609	1.45633	1.45656	1.45759	1.45764	1.45885	1.46116	1.46145	1.46388	1.46612	1.46987	90.26
D-FK95	模压前(-30℃/H)	1.43134	1.43170	1.43306	1.43396	1.43478	1.43559	1.43582	1.43603	1.43696	1.43700	1.43810	1.44019	1.44044	1.44264	1.44466	1.44803	95.10
	模压后	1.43033	1.43075	1.43223	1.43317	1.43399	1.43480	1.43503	1.43524	1.43617	1.43621	1.43730	1.43940	1.43966	1.44185	1.44386	1.44723	94.83
D-K9	模压前(-30℃/H)	1.50603	1.50673	1.50929	1.51094	1.51241	1.51384	1.51424	1.51461	1.51625	1.51633	1.51825	1.52190	1.52236	1.52621	1.52976	1.53574	64.06
	模压后	1.50444	1.50524	1.50804	1.50975	1.51123	1.51265	1.51305	1.51342	1.51504	1.51512	1.51703	1.52069	1.52115	1.52502	1.52858	1.53456	64.07
D-PK60	模压前(-30℃/H)	1.58112	1.58182	1.58444	1.58618	1.58775	1.58931	1.58974	1.59014	1.59193	1.59201	1.59412	1.59814	1.59864	1.60291	1.60684	1.61349	67.00
	模压后	1.57865	1.57943	1.58223	1.58401	1.58559	1.58714	1.58757	1.58797	1.58975	1.58983	1.59193	1.59596	1.59646	1.60073	1.60466	1.61131	66.87
D-PK62	模压前(-30℃/H)	1.60722	1.60793	1.61065	1.61249	1.61418	1.61586	1.61633	1.61676	1.61872	1.61881	1.62112	1.62555	1.62610	1.63084	1.63522	1.64265	63.85
	模压后	1.60546	1.6061	1.60866	1.61047	1.61215	1.61384	1.61431	1.61475	1.61671	1.61680	1.61912	1.62355	1.62410	1.62882	1.63320	1.64063	63.52
D-PK70	模压前(-30℃/H)	1.51542	1.51607	1.51845	1.51999	1.52136	1.52269	1.52306	1.52341	1.52493	1.52500	1.52679	1.53017	1.53058	1.53413	1.53738	1.54287	70.32
	模压后	1.51168	1.51234	1.51473	1.51627	1.51764	1.51897	1.51933	1.51968	1.52119	1.52126	1.52303	1.52638	1.52680	1.53033	1.53359	1.53908	70.35
D-ZK2N	模压前(-30℃/H)	1.57504	1.57579	1.57863	1.58054	1.58228	1.58399	1.58448	1.58492	1.58691	1.58700	1.58935	1.59384	1.59441	1.59918	1.60364	1.61145	59.59
	模压后	1.57321	1.57395	1.57677	1.57867	1.58040	1.58212	1.58260	1.58304	1.58503	1.58512	1.58747	1.59196	1.59252	1.59730	1.60177	1.60959	59.46
D-ZK3L	模压前(-30℃/H)	1.57711	1.57790	1.58083	1.58275	1.58448	1.58618	1.58665	1.58709	1.58904	1.58913	1.59142	1.59580	1.59634	1.60095	1.60520	1.61247	61.25
	模压后	1.57487	1.5757	1.57872	1.58068	1.58242	1.58412	1.58459	1.58503	1.58698	1.58707	1.58936	1.59373	1.59427	1.59890	1.60317	1.61040	61.09
D-ZK50	模压前(-30℃/H)	1.59586	1.59671	1.59986	1.60194	1.60380	1.60565	1.60616	1.60664	1.60876	1.60886	1.61136	1.61616	1.61676	1.62184	1.62655	1.63460	57.90
	模压后	1.59363	1.59448	1.59766	1.59974	1.60161	1.60345	1.60396	1.60444	1.60656	1.60666	1.60916	1.61395	1.61455	1.61964	1.62436	1.63241	57.78

### NHG低熔点玻璃模压前后谱线折射率对照参考值

牌号	分类	n1064	nt	ns	nA'	nr	nC	nC'	nHe-Ne	nD	nd	ne	nF	nF'	ng	nh	ni	ud
		1064.00	1013.98	852.11	768.19	706.52	656.27	643.85	632.8	589.29	587.56	546.07	486.13	479.99	435.84	404.66	365.01	
D-LaK6	模压前(-30℃/H)	1.67799	1.67895	1.68259	1.68506	1.68731	1.68955	1.69017	1.69076	1.69338	1.69350	1.69661	1.70258	1.70333	1.70973	1.71570	1.72593	53.20
	模压后	1.67527	1.67621	1.67985	1.68233	1.68460	1.68685	1.68748	1.68807	1.69069	1.69081	1.69391	1.69988	1.70063	1.70704	1.71302	1.72323	53.02
D-ZF10	模压前(-30℃/H)	1.66578	1.66698	1.67192	1.67552	1.67896	1.68249	1.68350	1.68445	1.68875	1.68893	1.69417	1.70466	1.70600	1.71785	1.72959	1.75178	31.08
	模压后	1.66203	1.66305	1.66763	1.67119	1.67463	1.67817	1.67917	1.68012	1.68438	1.68457	1.68974	1.70006	1.70138	1.71319	1.72497	1.74715	31.27
D-ZF52N	模压前(-30℃/H)	1.81108	1.81281	1.82015	1.82565	1.83096	1.83648	1.83806	1.83955	1.84635	1.84666	1.85504	1.87209	1.87431	1.89430	1.91469	1.95467	23.78
	模压后	1.80530	1.80724	1.81495	1.82050	1.82578	1.83123	1.83279	1.83426	1.84097	1.84127	1.84953	1.86637	1.86856	1.88830	1.90844	1.94807	23.94
D-LaF050	模压前(-30℃/H)	1.74994	1.75101	1.75515	1.75802	1.76066	1.76331	1.76406	1.76475	1.76787	1.76802	1.77173	1.77891	1.77980	1.78753	1.79475	1.80718	49.24
	模压后	1.74720	1.74826	1.75237	1.75522	1.75785	1.76049	1.76123	1.76193	1.76503	1.76517	1.76887	1.77604	1.77694	1.78466	1.79188	1.80431	49.21
D-LaF50	模压前(-30℃/H)	1.75436	1.75542	1.75961	1.76248	1.76513	1.76779	1.76854	1.76923	1.77236	1.77250	1.77622	1.78340	1.78430	1.79204	1.79927	1.81174	49.50
	模压后	1.75140	1.7525	1.75674	1.75963	1.76228	1.76494	1.76568	1.76638	1.76949	1.76963	1.77335	1.78054	1.78144	1.78918	1.79641	1.80888	49.34
D-LaF731	模压前(-30℃/H)	1.71080	1.71191	1.71635	1.71949	1.72243	1.72541	1.72625	1.72705	1.73061	1.73077	1.73505	1.74345	1.74452	1.75376	1.76260	1.77835	40.50
	模压后	1.70963	1.71048	1.71435	1.71738	1.72031	1.72331	1.72416	1.72495	1.72853	1.72869	1.73298	1.74134	1.74239	1.75159	1.76042	1.77618	40.42
D-LaF743	模压前(-30℃/H)	1.72590	1.72692	1.73091	1.73366	1.73621	1.73876	1.73948	1.74016	1.74317	1.74330	1.74689	1.75383	1.75470	1.76215	1.76911	1.78110	49.33
	模压后	1.72297	1.72405	1.72817	1.73097	1.73353	1.73609	1.73680	1.73747	1.74048	1.74061	1.74418	1.75111	1.75198	1.75945	1.76642	1.77841	49.31
D-ZLaF52L	模压前(-30℃/H)	1.78422	1.78543	1.79027	1.79371	1.79694	1.80022	1.80114	1.80201	1.80592	1.80610	1.81080	1.82002	1.82117	1.83126	1.84085	1.85784	40.73
	模压后	1.78160	1.78279	1.78761	1.79105	1.79428	1.79755	1.79848	1.79935	1.80325	1.80342	1.80811	1.81730	1.81846	1.82853	1.83812	1.85508	40.68
D-ZLaF52N	模压前(-30℃/H)	1.78814	1.78935	1.79418	1.79762	1.80084	1.80411	1.80505	1.80591	1.80982	1.81000	1.81469	1.82387	1.82502	1.83508	1.84465	1.86160	41.00
	模压后	1.78552	1.78671	1.79151	1.79495	1.79817	1.80145	1.80237	1.80324	1.80714	1.80731	1.81199	1.82116	1.82232	1.83236	1.84193	1.85887	40.96
D-ZLaF52N-M170	模压前(-30℃/H)	1.78654	1.78774	1.79256	1.79599	1.79921	1.80247	1.80340	1.80427	1.80817	1.80834	1.81303	1.82223	1.82339	1.83343	1.84298	1.85982	40.92
	模压后	1.78392	1.7851	1.78989	1.79332	1.79654	1.79980	1.80073	1.80159	1.80549	1.80566	1.81035	1.81951	1.82067	1.83070	1.84024	1.85709	40.88

### NHG低熔点玻璃模压前后谱线折射率对照参考值

牌号	分类	n1064	nt	ns	nA'	nr	nC	nC'	nHe-Ne	nD	nd	ne	nF	nF'	ng	nh	ni	vd
		1064.00	1013.98	852.11	768.19	706.52	656.27	643.85	632.8	589.29	587.56	546.07	486.13	479.99	435.84	404.66	365.01	
D-ZLaF53	模压前(-30℃/H)	1.81004	1.81137	1.81671	1.82054	1.82414	1.82781	1.82884	1.82981	1.83421	1.83441	1.83972	1.85019	1.85152	1.86316	1.87437	1.89451	37.28
	模压后	1.80674	1.80798	1.81318	1.81699	1.82060	1.82428	1.82531	1.82629	1.83069	1.83088	1.83618	1.84662	1.84795	1.85957	1.87080	1.89094	37.19
D-ZLaF814	模压前(-30℃/H)	1.79076	1.79207	1.79734	1.80110	1.80465	1.80825	1.80927	1.81023	1.81455	1.81474	1.81995	1.83025	1.83156	1.84293	1.85388	1.87363	37.03
	模压后	1.78663	1.78814	1.79384	1.79769	1.80124	1.80482	1.80583	1.80678	1.81107	1.81126	1.81645	1.82670	1.82801	1.83938	1.85032	1.87007	37.08
D-ZLaF851	模压前(-30℃/H)	1.82801	1.82929	1.83442	1.83808	1.84154	1.84505	1.84604	1.84697	1.85116	1.85135	1.85639	1.86628	1.86753	1.87838	1.88871	1.90699	40.10
	模压后	1.82492	1.82625	1.83154	1.83525	1.83871	1.84222	1.84321	1.84414	1.84832	1.84851	1.85353	1.86340	1.86465	1.87549	1.88582	1.90410	40.06