

H-LaK53A 755523	$n_d = 1.75500$	$v_d = 52.32$	$n_F - n_C = 0.014430$
	$n_e = 1.75844$	$v_e = 52.09$	$n_{F'} - n_{C'} = 0.014561$

Refractive Indices		
	$\lambda(\text{nm})$	n_λ
n_{2325}	2325.42	1.71389
n_{1970}	1970.09	1.72137
n_{1530}	1529.58	1.72950
n_{1129}	1128.64	1.73661
n_t	1013.98	1.73893
n_s	852.11	1.74293
$n_{A'}$	768.19	1.74566
n_r	706.52	1.74815
n_C	656.27	1.75063
$n_{C'}$	643.85	1.75132
$n_{\text{He-Ne}}$	632.80	1.75197
n_D	589.29	1.75487
n_d	587.56	1.75500
n_e	546.07	1.75844
n_F	486.13	1.76506
$n_{F'}$	479.99	1.76588
n_g	435.84	1.77295
n_h	404.66	1.77953
n_i	365.01	1.79081

Constants of Dispersion Formula	
A_0	3.01906956E+00
A_1	-1.58184620E-02
A_2	2.09047144E-02
A_3	8.46561491E-04
A_4	-6.18209745E-05
A_5	3.65072914E-06

Relative Partial Dispersions			
$P_{d,C}$	0.3028	$P'_{d,C'}$	0.2527
$P_{e,d}$	0.2384	$P'_{e,d}$	0.2363
$P_{g,F}$	0.5468	$P'_{g,F'}$	0.4856

Range of Temperature (°C)	Temperature Coefficients of Refractive Index						
	dn/dt relative ($10^{-6} / ^\circ\text{C}$)						
	t	C'	He-Ne	D	e	F'	g
-40 ~ -20	3.4	3.8	3.8	4.0	4.2	4.6	5.0
-20 ~ 0	3.3	3.8	3.9	4.0	4.2	4.6	5.0
0 ~ 20	3.3	3.8	3.9	4.0	4.2	4.7	5.1
20 ~ 40	3.3	3.9	3.9	4.1	4.3	4.7	5.2
40 ~ 60	3.4	4.0	4.0	4.2	4.4	4.8	5.3
60 ~ 80	3.5	4.1	4.2	4.3	4.5	5.0	5.5

Chemical Properties (grade)	
RC(S)	1
RA(S)	2
D_W	1
D_A	3
$R_{OH}(S)$	1
RP(S)	1

Thermal Properties	
$T_g(^\circ\text{C})$	681
$T_s(^\circ\text{C})$	708
$T_{10}^{14.5}(^\circ\text{C})$	631
$T_{10}^{13}(^\circ\text{C})$	652
$\alpha_{-50/80^\circ\text{C}}(10^{-7}/\text{K})$	57
$\alpha_{100/300^\circ\text{C}}(10^{-7}/\text{K})$	72

Mechanical Properties	
HK(10^7Pa)	718
F_A	58
$E(10^7\text{Pa})$	10998
$G(10^7\text{Pa})$	4253
μ	0.293
$B(\text{nm}/\text{cm}/10^5\text{Pa})$	1.400

Density	
$\rho(\text{g}/\text{cm}^3)$	4.24

Deviation of Relative Partial Dispersions	
$\Delta P_{F,e}$	-0.0026
$\Delta P_{g,F}$	-0.0099
$\Delta P_{C,t}$	0.0172
$\Delta P_{C,s}$	0.0076

Internal Transmittance		
$\lambda(\text{nm})$	$\tau_5\text{mm}$	$\tau_{10}\text{mm}$
2400	0.778	0.605
2200	0.934	0.872
2000	0.990	0.980
1800	0.999	0.998
1600	0.999	0.998
1400	0.999	0.998
1200	0.999	0.998
1060	0.999	0.998
1000	0.999	0.998
900	0.999	0.998
850	0.999	0.998
800	0.999	0.998
750	0.999	0.998
700	0.999	0.998
650	0.999	0.998
600	0.999	0.998
550	0.999	0.998
500	0.999	0.998
480	0.999	0.998
460	0.999	0.998
440	0.997	0.994
420	0.995	0.989
400	0.992	0.984
390	0.989	0.978
380	0.984	0.968
370	0.975	0.950
360	0.957	0.918
350	0.934	0.873
340	0.897	0.805
330	0.846	0.715
320	0.779	0.607
310	0.672	0.450
300	0.606	0.367
290	0.515	0.266
280	0.354	0.129

Coloration Code	
$\lambda_{80}(\lambda_{70})/\lambda_5$	370/280

Coloration of Internal Transmittance	
$\lambda\tau_{80}/\lambda\tau_5$	340/276