

H-ZLaF2 803468	$n_d = 1.80279$	$v_d = 46.76$	$n_F - n_C = 0.017168$
	$n_e = 1.80687$	$v_e = 46.52$	$n_{F'} - n_{C'} = 0.017345$

Refractive Indices		
	$\lambda(\text{nm})$	n_λ
n_{2325}	2325.42	1.75864
n_{1970}	1970.09	1.76610
n_{1530}	1529.58	1.77430
n_{1129}	1128.64	1.78174
n_t	1013.98	1.78426
n_s	852.11	1.78874
$n_{A'}$	768.19	1.79184
n_r	706.52	1.79473
n_C	656.27	1.79763
$n_{C'}$	643.85	1.79845
$n_{\text{He-Ne}}$	632.80	1.79921
n_D	589.29	1.80264
n_d	587.56	1.80279
n_e	546.07	1.80687
n_F	486.13	1.81480
$n_{F'}$	479.99	1.81579
n_g	435.84	1.82438
n_h	404.66	1.83241
n_i	365.01	1.84644

Constants of Dispersion Formula	
A_0	3.17454812E+00
A_1	-1.59776958E-02
A_2	2.51277775E-02
A_3	1.18617161E-03
A_4	-8.90435226E-05
A_5	6.03380469E-06

Relative Partial Dispersions			
$P_{d,C}$	0.3005	$P'_{d,C'}$	0.2503
$P_{e,d}$	0.2376	$P'_{e,d}$	0.2353
$P_{g,F}$	0.5579	$P'_{g,F'}$	0.4954

Range of Temperature (°C)	Temperature Coefficients of Refractive Index						
	dn/dt relative (10 ⁻⁶ / °C)						
	t	C'	He-Ne	D	e	F'	g
-40 ~ -20	3.7	4.3	4.4	4.5	4.8	5.3	5.9
-20 ~ 0	3.6	4.3	4.3	4.5	4.7	5.3	5.9
0 ~ 20	3.7	4.3	4.4	4.6	4.8	5.4	6.0
20 ~ 40	3.8	4.5	4.5	4.7	5.0	5.6	6.2
40 ~ 60	3.9	4.6	4.7	4.9	5.2	5.8	6.5
60 ~ 80	4.1	4.8	4.9	5.1	5.4	6.1	6.7

Chemical Properties (grade)	
RC(S)	1
RA(S)	1
D _W	1
D _A	3
R _{OH} (S)	1
RP(S)	1

Thermal Properties	
T _g (°C)	675
T _s (°C)	703
T ₁₀ ^{14.5} (°C)	612
T ₁₀ ¹³ (°C)	648
$\alpha_{-50/80^\circ\text{C}}$ (10 ⁻⁷ /K)	59
$\alpha_{100/300^\circ\text{C}}$ (10 ⁻⁷ /K)	74

Mechanical Properties	
HK(10 ⁷ Pa)	702
F _A	68
E(10 ⁷ Pa)	12357
G(10 ⁷ Pa)	4782
μ	0.292
B(nm/cm/10 ⁵ Pa)	1.690

Density	
ρ (g/cm ³)	4.68

Deviation of Relative Partial Dispersions	
$\Delta P_{F,e}$	-0.0025
$\Delta P_{g,F}$	-0.0080
$\Delta P_{C,t}$	0.0120
$\Delta P_{C,s}$	0.0051

Internal Transmittance		
$\lambda(\text{nm})$	$\tau_5\text{mm}$	$\tau_{10}\text{mm}$
2400	0.826	0.682
2200	0.959	0.920
2000	0.993	0.986
1800	0.999	0.998
1600	0.999	0.998
1400	0.999	0.998
1200	0.999	0.998
1060	0.999	0.998
1000	0.999	0.998
900	0.999	0.998
850	0.999	0.998
800	0.999	0.998
750	0.999	0.998
700	0.999	0.998
650	0.999	0.998
600	0.997	0.994
550	0.996	0.992
500	0.995	0.990
480	0.994	0.988
460	0.994	0.988
440	0.994	0.988
420	0.993	0.986
400	0.988	0.976
390	0.983	0.973
380	0.975	0.956
370	0.959	0.925
360	0.929	0.870
350	0.881	0.781
340	0.791	0.629
330	0.620	0.383
320	0.322	0.103
310	0.043	0.007
300		
290		
280		

Coloration Code	
$\lambda_{80}(\lambda_{70})/\lambda_5$	380/320

Coloration of Internal Transmittance	
$\lambda\tau_{80}/\lambda\tau_5$	