

<b>D-ZLaF52N</b>	<b>810410</b>	$n_d = 1.81000$	$v_d = 41.00$	$n_F - n_C = 0.019758$
		$n_e = 1.81469$	$v_e = 40.80$	$n_{F'} - n_{C'} = 0.019970$

Refractive Indices		
	$\lambda$ (nm)	$n_\lambda$
$n_{2325}$	2325.42	1.76475
$n_{1970}$	1970.09	1.77159
$n_{1530}$	1529.58	1.77930
$n_{1129}$	1128.64	1.78671
$n_{1064}$	1064.00	1.78814
$n_t$	1013.98	1.78935
$n_s$	852.11	1.79418
$n_{A'}$	768.19	1.79762
$n_f$	706.52	1.80084
$n_C$	656.27	1.80411
$n_{C'}$	643.85	1.80505
$n_{He-Ne}$	632.80	1.80591
$n_D$	589.29	1.80982
$n_d$	587.56	1.81000
$n_e$	546.07	1.81469
$n_F$	486.13	1.82387
$n_{F'}$	479.99	1.82502
$n_g$	435.84	1.83508
$n_h$	404.66	1.84465
$n_i$	365.01	1.86160

Relative Partial Dispersion	
$P_{d,C}$	0.2981
$P_{e,d}$	0.2374
$P_{g,F}$	0.5674
$P'_{d,c'}$	0.2479
$P'_{e,d}$	0.2349
$P'_{g,F'}$	0.5038

Chemical Properties (grade)	
RC (S)	1
RA (S)	3
D <sub>w</sub>	1
D <sub>A</sub>	3
R <sub>OH</sub> (S)	1
RP (S)	2
CR	1

Internal Transmittance		
$\lambda$ (nm)	$\tau_{5mm}$	$\tau_{10mm}$
2400	0.850	0.723
2200	0.956	0.914
2000	0.975	0.951
1800	0.988	0.976
1600	0.999	0.998
1400	0.999	0.998
1200	0.999	0.998
1060	0.999	0.998
1000	0.999	0.998
950	0.999	0.998
900	0.999	0.998
850	0.999	0.998
800	0.999	0.998
750	0.999	0.998
700	0.999	0.998
650	0.999	0.998
600	0.999	0.997
550	0.999	0.997
500	0.998	0.996
480	0.996	0.996
460	0.994	0.993
440	0.992	0.988
420	0.990	0.974
400	0.982	0.959
390	0.975	0.944
380	0.963	0.919
370	0.940	0.876
360	0.894	0.795
350	0.816	0.662
340	0.646	0.415
330	0.320	0.103
320		
310		
300		
290		
280		

Deviation of Relative Partial Dispersions	
$\Delta P_{F,e}$	-0.0029
$\Delta P_{g,F}$	-0.0081
$\Delta P_{C,t}$	0.0083
$\Delta P_{C,s}$	0.0038

Expansion Coefficient $\alpha$ ( $\times 10^{-7}/K$ )	
$^{\circ}C$	$\alpha$
-50/-40	51
-40/-30	54
-30/-20	56
-20/-10	58
-10/0	59
0/10	60
10/20	61
20/30	62
30/40	63
40/50	64
50/60	64
60/70	64
70/80	65
80/90	66
90/100	67
100/110	68
110/120	69
120/130	70
130/140	71
140/150	72
150/160	73

Thermal Properties	
T <sub>g</sub> ( $^{\circ}C$ )	548
T <sub>s</sub> ( $^{\circ}C$ )	578
T <sub>10</sub> <sup>14.5</sup> ( $^{\circ}C$ )	510
T <sub>10</sub> <sup>13</sup> ( $^{\circ}C$ )	529
$\alpha_{-50/80^{\circ}C}$ ( $10^{-7}/K$ )	60
$\alpha_{100/300^{\circ}C}$ ( $10^{-7}/K$ )	79
$\lambda$ (W/(m K))	0.98
$\beta_d$	140

Constants of Dispersion Formula	
A <sub>0</sub>	3.18681101E+00
A <sub>1</sub>	-1.44191920E-02
A <sub>2</sub>	2.95460135E-02
A <sub>3</sub>	1.15252022E-03
A <sub>4</sub>	-5.90862778E-05
A <sub>5</sub>	5.97442323E-06

Mechanical Properties	
HK ( $10^7$ Pa)	625
F <sub>A</sub>	91
E (GPa)	114.4
G (GPa)	42.6
$\mu$	0.343
$\sigma_b$ (MPa)	81
B ( $10^{-12}$ /Pa)	2.17

Density	Solarization
$\rho$ (g/cm <sup>3</sup> )	$\Delta\lambda$ (%)
4.47	-0.6

Range of Temperature ( $^{\circ}C$ )	Temperature Coefficients of Refractive Index									
	dn/dt relative ( $\times 10^{-6} / ^{\circ}C$ )									
	t	s	C	C'	He-Ne	d	e	F	F'	g
-60 ~ -40	5.1	5.6	6.7	6.9	7.0	7.2	7.9	9.7	9.8	11.2
-40 ~ -20	5.6	6.2	7.1	7.2	7.3	7.6	8.3	10.1	10.1	11.6
-20 ~ 0	6.0	6.7	7.4	7.6	7.8	8.0	8.6	10.4	10.6	12.0
0 ~ 20	6.5	7.2	7.6	7.9	8.2	8.3	8.8	10.6	10.8	12.3
20 ~ 40	6.7	7.5	7.8	8.1	8.2	8.6	8.9	10.8	11.0	12.5
40 ~ 60	7.0	7.8	8.0	8.2	8.4	8.8	9.0	11.0	11.2	12.7
60 ~ 80	7.2	8.0	8.2	8.3	8.4	9.0	9.2	11.2	11.4	12.9
80 ~ 100	7.4	8.2	8.4	8.4	8.6	9.2	9.4	11.4	11.5	12.9
100 ~ 120	7.7	8.3	8.5	8.5	8.7	9.3	9.6	11.5	11.6	13.0
120 ~ 140	8.0	8.4	8.6	8.6	8.9	9.3	9.7	11.6	11.7	13.1
140 ~ 160	8.3	8.6	8.6	8.6	9.2	9.4	9.8	11.7	11.9	13.2

Coloration Code	
$\lambda_{80}(\lambda_{70})/\lambda_5$	395/330
Coloration of Internal Transmittance	
$\lambda\tau_{80}/\lambda\tau_5$	360/327

Constants of dn/dt		
D <sub>0</sub>	D <sub>1</sub>	D <sub>2</sub>
6.96E-06	2.21E-08	-4.66E-11
E <sub>0</sub>	E <sub>1</sub>	$\lambda_{TK}$
9.87E-07	-3.77E-10	2.98E-01