

| | | | | |
|-------------------|---------------|-----------------|---------------|------------------------|
| H-ZLaF70GT | 904313 | $n_d = 1.90366$ | $v_d = 31.32$ | $n_F - n_C = 0.028857$ |
| | | $n_e = 1.91048$ | $v_e = 31.08$ | $n_F - n_C = 0.029295$ |

| Refractive Indices | | |
|--------------------|----------------|-------------|
| | λ (nm) | n_λ |
| n_{2325} | 2325.42 | 1.84663 |
| n_{1970} | 1970.09 | 1.85408 |
| n_{1530} | 1529.58 | 1.86274 |
| n_{1129} | 1128.64 | 1.87166 |
| n_{1064} | 1064.00 | 1.87348 |
| n_t | 1013.98 | 1.87504 |
| n_s | 852.11 | 1.88144 |
| $n_{A'}$ | 768.19 | 1.88615 |
| n_f | 706.52 | 1.89065 |
| n_C | 656.27 | 1.89526 |
| $n_{C'}$ | 643.85 | 1.89657 |
| n_{He-Ne} | 632.80 | 1.89781 |
| n_D | 589.29 | 1.90341 |
| n_d | 587.56 | 1.90366 |
| n_e | 546.07 | 1.91048 |
| n_F | 486.13 | 1.92412 |
| $n_{F'}$ | 479.99 | 1.92587 |
| n_g | 435.84 | 1.94128 |
| n_h | 404.66 | 1.95645 |
| n_i | 365.01 | 1.98472 |
| | | |
| | | |

| Relative Partial Dispersion | |
|-----------------------------|--------|
| $P_{d,C}$ | 0.2911 |
| $P_{e,d}$ | 0.2363 |
| $P_{g,F}$ | 0.5947 |
| $P'_{d,c'}$ | 0.2420 |
| $P'_{e,d}$ | 0.2328 |
| $P'_{g,F'}$ | 0.5260 |
| | |

| Chemical Properties (grade) | |
|-----------------------------|---|
| RC (S) | 1 |
| RA (S) | 2 |
| D _w | 1 |
| D _A | 2 |
| R _{OH} (S) | 1 |
| RP (S) | 1 |
| CR | 1 |

| Internal Transmittance | | |
|------------------------|--------------|---------------|
| λ (nm) | τ_{5mm} | τ_{10mm} |
| 2400 | 0.867 | 0.751 |
| 2200 | 0.947 | 0.897 |
| 2000 | 0.982 | 0.964 |
| 1800 | 0.992 | 0.984 |
| 1600 | 0.997 | 0.995 |
| 1400 | 0.998 | 0.996 |
| 1200 | 0.999 | 0.997 |
| 1060 | 0.999 | 0.998 |
| 1000 | 0.999 | 0.998 |
| 950 | 0.999 | 0.998 |
| 900 | 0.999 | 0.998 |
| 850 | 0.999 | 0.998 |
| 800 | 0.999 | 0.998 |
| 750 | 0.999 | 0.998 |
| 700 | 0.999 | 0.998 |
| 650 | 0.999 | 0.998 |
| 600 | 0.998 | 0.997 |
| 550 | 0.997 | 0.995 |
| 500 | 0.994 | 0.988 |
| 480 | 0.991 | 0.983 |
| 460 | 0.987 | 0.975 |
| 440 | 0.982 | 0.964 |
| 420 | 0.971 | 0.942 |
| 400 | 0.941 | 0.886 |
| 390 | 0.904 | 0.817 |
| 380 | 0.817 | 0.668 |
| 370 | 0.611 | 0.374 |
| 360 | 0.268 | 0.073 |
| 350 | | |
| 340 | | |
| 330 | | |
| 320 | | |
| 310 | | |
| 300 | | |
| 290 | | |
| 280 | | |

| Deviation of Relative Partial Dispersions | |
|---|---------|
| $\Delta P_{F,e}$ | -0.0002 |
| $\Delta P_{g,F}$ | 0.0031 |
| $\Delta P_{C,t}$ | 0.0088 |
| $\Delta P_{C,s}$ | 0.0033 |

| Expansion Coefficient α ($\times 10^{-7}/K$) | |
|---|----------|
| $^{\circ}C$ | α |
| -50/-40 | 59 |
| -40/-30 | 61 |
| -30/-20 | 62 |
| -20/-10 | 64 |
| -10/0 | 65 |
| 0/10 | 66 |
| 10/20 | 66 |
| 20/30 | 67 |
| 30/40 | 68 |
| 40/50 | 68 |
| 50/60 | 69 |
| 60/70 | 70 |
| 70/80 | 70 |
| 80/90 | 71 |
| 90/100 | 71 |
| 100/110 | 73 |
| 110/120 | 74 |
| 120/130 | 75 |
| 130/140 | 76 |
| 140/150 | 77 |
| 150/160 | 77 |

| Thermal Properties | |
|---|------|
| T _g ($^{\circ}C$) | 679 |
| T _s ($^{\circ}C$) | 707 |
| T ₁₀ ^{14.5} ($^{\circ}C$) | 595 |
| T ₁₀ ¹³ ($^{\circ}C$) | 643 |
| $\alpha_{-50/80^{\circ}C}$ ($10^{-7}/K$) | 66 |
| $\alpha_{100/300^{\circ}C}$ ($10^{-7}/K$) | 82 |
| λ (W/(m K)) | 1.04 |

| Constants of Dispersion Formula | |
|---------------------------------|-----------------|
| A ₀ | 3.48854243E+00 |
| A ₁ | -1.59982726E-02 |
| A ₂ | 4.28443509E-02 |
| A ₃ | 2.18903241E-03 |
| A ₄ | -1.15672643E-04 |
| A ₅ | 1.78697063E-05 |

| Mechanical Properties | |
|-----------------------|-------|
| HK (10^7 Pa) | 640 |
| F _A | 80 |
| E (GPa) | 117.6 |
| G (GPa) | 45.6 |
| μ | 0.288 |
| σ_b (MPa) | 63 |
| B (10^{-12} /Pa) | 2.01 |

| Density | | Solarization | |
|-----------------------------|------|---------------------|------|
| ρ (g/cm ³) | 4.54 | $\Delta\lambda$ (%) | -0.4 |

| Range of Temperature ($^{\circ}C$) | Temperature Coefficients of Refractive Index | | | | | | | | | |
|--------------------------------------|---|-----|-----|-----|-------|-----|-----|-----|-----|-----|
| | dn/dt relative ($\times 10^{-6} / ^{\circ}C$) | | | | | | | | | |
| | t | s | C | C' | He-Ne | d | e | F | F' | g |
| -60 ~ -40 | 2.4 | 2.8 | 3.3 | 3.4 | 3.4 | 3.6 | 4.0 | 5.1 | 5.1 | 6.4 |
| -40 ~ -20 | 2.4 | 2.9 | 3.4 | 3.4 | 3.5 | 3.8 | 4.3 | 5.2 | 5.3 | 6.5 |
| -20 ~ 0 | 2.4 | 3.1 | 3.5 | 3.5 | 3.6 | 4.0 | 4.5 | 5.4 | 5.5 | 6.8 |
| 0 ~ 20 | 2.5 | 3.3 | 3.6 | 3.6 | 3.7 | 4.1 | 4.6 | 5.6 | 5.7 | 7.1 |
| 20 ~ 40 | 2.6 | 3.4 | 3.7 | 3.7 | 3.8 | 4.2 | 4.7 | 5.9 | 6.0 | 7.5 |
| 40 ~ 60 | 2.7 | 3.4 | 3.8 | 3.9 | 3.9 | 4.3 | 4.9 | 6.2 | 6.2 | 7.7 |
| 60 ~ 80 | 2.7 | 3.5 | 4.0 | 4.0 | 4.1 | 4.6 | 5.1 | 6.5 | 6.5 | 8.0 |
| 80 ~ 100 | 2.9 | 3.5 | 4.1 | 4.1 | 4.2 | 4.8 | 5.2 | 6.8 | 6.8 | 8.2 |
| 100 ~ 120 | 3.1 | 3.7 | 4.2 | 4.2 | 4.4 | 4.9 | 5.2 | 7.0 | 7.0 | 8.3 |
| 120 ~ 140 | 3.3 | 3.9 | 4.3 | 4.4 | 4.6 | 5.1 | 5.4 | 7.1 | 7.2 | 8.4 |
| 140 ~ 160 | 3.5 | 4.0 | 4.4 | 4.4 | 4.6 | 5.3 | 5.6 | 7.2 | 7.3 | 8.6 |

| Coloration Code | |
|--|-----------|
| $\lambda_{80}(\lambda_{70})/\lambda_5$ | (395)/361 |
| Coloration of Internal Transmittance | |
| $\lambda\tau_{80}/\lambda\tau_5$ | 389/360 |

| Constants of dn/dt | | |
|--------------------|----------------|----------------|
| D ₀ | D ₁ | D ₂ |
| 6.13E-07 | 1.29E-08 | -2.38E-11 |
| E ₀ | E ₁ | λ_{TK} |
| 7.62E-07 | 6.31E-10 | 2.84E-01 |